



EV-40D

2 Stage Crosslinked Polyethylene

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be sued for specification development.

Corporate Headquarters:
1806 Conant St.
Elkhart, IN 46516
www.worldwidefoam.com
Info@worldwidefoam.com



Ph: 574-968-8268 Fax: 574-970-0926

PHYSICAL PROPERTIES		TEST METHOD	VALUES	USA UNITS	VALUES	METRIC UNITS
Density - Nominal		ASTM D3575	4	lb/ft ³	64	kg/m ³
Tensile Strength		ASTM D3575	70	psi	483	kPa
Tear Strength		ASTM D3575	18	lb/in	321	kg/m
Elongation		ASTM D3575	450	%	450	%
Firmness		ASTM D2240	28	Asker C	28	Asker C
Compressive Stress						
Compression Set	50% 24hr	ASTM D3575 Suffix B	<12	%	<12	%
Compression Strength	25%	ASTM D3575 Suffix D	10	psi	69	kPa
	50%		18		124	
Working Temperature Range		Internal Test	-40 to 225	°F	-40 to 107	°C
Water Absorption 7 Days		ASTM-D1667	.0123	Lbs./sq.ft		
Flammability		FMVSS302	Pass	Pass/Fail	2.01"/min	Burn Rate

For bun size and color availability, please see the color and sizing chart, or contact us at info@worldwidefoam.com or visit www.worldwidefoam.com

*Testing done according to ASTM D3575 & ASTM C177 (thermal conductivity) standards.

The data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.