

GOMSPOR C-4305

INOAC CORPORATION

## 1. Characteristics

The product is a chloroprene rubber foam with mid-level hardness.

## 2. Product Specification

Block

Item	Thickness (mm)	Width (mm)	Length (mm)
GOMSPOR	30	1000	1000
C-4305	30	1000	1300
	30	1000	2000

Sliced Seet

Item	Thickness (mm)	Width (mm)	Length (mm)
GOMSPOR	0.5~28	1000	1000
C-4305	1~28	1000	1300
	1~28	1000	2000

## 3. Pyhsical Properties

Sample	GOMSPOR C-4305			
	Unit	Result	Specification	Test Method
Pyhsical Properties				
Hardness (Type C)		24	25±5	Asker-C
Tensile Strength	MPa	0.59	0.49 or more	JIS K 6767
Elongation	%	220	150 or more	JIS K 6767
Apparent density	g/cm <sup>3</sup>	0.19	0.19±0.03	JIS K 6767
Compression set ratio	%	15.3	30 or less	ASTM D 1056
Heat shrinkage ratio	%	0.5	1.5 or less	70°C×4Hours
Absorption	%	1.4	5 or less	ASTM D 1056
25%compressed load	kPa	71.1	61.9~93.2	ASTM D 1056

※Test method is based on Inoac's "Physical Testing Standard for Closed—Cell Rubber Sponge"