

GOMSPOR C-4315

INOAC CORPORATION

1. Characteristics

The product is a gray rubber sponge with chloroprene rubber.

2. Product Specification

Block

Item	Thickness (mm)	Width (mm)	Length (mm)
GOMSPOR C-4315	30	1000	1000

Sliced Seet

Item	Thickness (mm)	Width (mm)	Length (mm)
GOMSPOR C-4315	1~28	1000	1000

3. Standard Physical Property

Sample	GOMSPOR C-4315			
	Unit	Result	Specification	Test Method
Pyhsical Properties				
Hardness (Type C)		17	20±5	Asker-C
Tensile Strength	MPa	0.59	0.49 or more	JIS K 6767
Elongation	%	200	150 or more	JIS K 6767
Apparent density	g/cm ³	0.17	0.19±0.03	JIS K 6767
Compression set ratio	%	23.4	30 or less	ASTM D 1056
Heat shrinkage ratio	%	0.2	1.5 or less	70°C×4Hours
Water Absorption	%	3.1	5 or less	ASTM D 1056
25%compressed load	kPa	54.6	29.4~68.6	ASTM D 1056

※Test method is based on Inoac's "Physical Testing Standard for Closed—Cell Rubber Sponge"