

SUBMITTAL SHEET (effective 10/31/08)

**IVC Continuous Rolls/Sheets**

Physical Properties

Polymer	PVC/NBR/CR	
Color	Black	
Classifications		
ASTM D 1056-68		SCE41/42
ASTM D 1056-07		2C1/2C2
Suffix Requirements		
		C1, F1, M
1. 25% Compression Resistance (psi)	ASTM D 1056	4.0 – 6.0
2. 50% Compression Set (%)	ASTM D 1056	40 max.
3. Density (lb/ft <sup>3</sup> )	ASTM D 1056	4.0 – 5.5
4. Water Absorption (lb/ft <sup>2</sup> )	ASTM D 1056	10 max.
5. Tensile (psi)	ASTM D 412	50 min.
6. Elongation (%)	ASTM D 412	100 min.
7. Flammability (1)		
FMVSS302	0 Burn Rate	Pass
UL 94	HF-1 @ 1/16"	Pass
UL 94	V-0 @ 1/2"	Pass
FAR 25.853 a(2003)	@ 1/4"	Pass
8. Temperature Use °F: (2)		
	ASTM D 1056	Cold Crack High (3)
		-40°F 200
Standard Roll Widths (in)		
		54" or 60"
Maximum Gauge (in)		
		1.25"

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

NBR – Acrylonitrile Butadiene Rubber

PVC – Polyvinyl Chloride

CR – Chloroprene (Neoprene®)

Minimum gauge for skin two sided products is 3/4"

Other gauges and widths may be available. Please contact Customer Service.

Note: SAEJ 18 is equivalent to ASTM D-1056

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 1004 Keisler Road • Conover NC 26813

email: info.us@armacell.com • www.armacell.com

Conover, NC • 800-992-9116 or 919-304-3846 ext 3110 • fax: 828-465-3199

Mebane, NC • 800-973-0490 or 919-304-3846 ext 3972 • fax: 919-304-3847

© 2008 Armacell LLC

IIVC	01	10	08	NA	NA
------	----	----	----	----	----

ALL ARMACELL FACILITIES IN NORTH AMERICA ARE  
ISO 9001:2000 OR ISO/TS 16949:2002 CERTIFIED