



American National Rubber

PO Box 877 ** Ceredo, West Virginia 25507 ** Telephone: 1-800-624-3410 ** Fax: 304-453-2347

DATA SHEET

NEOPRENE/EPDM/SBR BLEND

4111-N

| | | |
|--|-------------------------------|--------------|
| Color: | | Black |
| Specifications: | ASTM D-1056-00 | 2A1 |
| | ASTM D-1056-67 ⁽¹⁾ | SCE 41 |
| | SAE J18-02 | 2A1 |
| | GM 6086M ⁽³⁾ | II |
| | GMN11106 ⁽³⁾ | II |
| 25% Compression Deflection (PSI) | | 2-5 |
| Shore 00 Durometer (Approximate) | | 30 - 50 |
| Density (Approximate p.c.f.) | | 7 - 11 |
| Water Absorption By Weight | | 5% |
| Temperature Range | | -70 to 225 F |
| Weather Resistance: | UV | Fair |
| | Ozone | Good |
| Accelerated Linear Shrinkage (Typical) | | 5% |
| Tensile Strength (Typical) | | 50 PSI |
| Elongation (Typical) | | 150% |
| Flammability: | FM VSS No. 302 | Pass |

(1)Obsolete specification listed for reference only. ANR certifies to most recent revision of ASTM D-1056 and SAE J18.

(3)Certain sections of this specification will not apply to all products. Contact Customer Service for details.

American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.